

MIXING RATIOS



Apple R Foam Resin

Sets	Water	Resin Bags
1	38	4
3/4	28.5	3
1/2	19	2
1/4	9.5	1

Leave 2 gallons short upon mixing to clean mixing hopper

Apple R Foam Foaming Agent Catalyst (FAC)

Sets	Water	FAC Gallons
1	47	8
3/4	35.25	6
1/2	23.5	4
1/4	11.75	2

Approximate Square Foot Coverage 2x4 empty cavity

1 Set	1050
3/4 Set	787
1/2 Set	525
1/4 Set	262

***** 1 set of foam equals 55 gallons of Resin and 55 gallons of Foaming agent catalyst